

ADDcure® 9960

ADDcure 9960 (2,4,6-tris(dimethylaminomethyl)phenol) is used as accelerator for epoxy systems based on polyamides, polyamides adduct and amino adduct. The suggested percentage is around 5-10% on the total amount of curing agent.

CHEMICAL – PHYSICAL PROPERTIES

Appearance:	clear
Active content:	100 %
Colour Gardner:	7 max
Brookfield viscosity (mPa.s a 25°C):	150 - 500
Combustion point:	140°C
Boiling point:	250°C

HANDLING AND STORAGE

ADDcure curing agent may absorb moisture and CO₂ if drums are not well sealed. ADDcure curing agents should be stored in dry place at a temperature between 5 and 35°C; in these conditions, shelf life is 1 year.

Lower temperature may increase the viscosity (reversible) and induce haziness

ADDcure curing agents and epoxy resin must be mixed just before application; avoid contact with eyes and skin, do not inhale vapours, wear protective clothes, glasses and gloves. Use only with adequate ventilation.

For further information, read MATERIAL SAFETY DATA SHEET

What is indicated in this data sheet comes from our tests and it is offered in good faith for the benefit of our customers. The Company, however, cannot assume any liability or risk in the use of its products, since the conditions of use are beyond our control. Statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patent.

Edition: May 2012

This version cancels all previous versions