

ADDpox[®] SR 5198

High molecular weight solid Epoxy Resin

General	ADDpox [®] SR 5198 is a high melt viscosity, unmodified epoxy resin based on bisphenol A, designed for high quality industrial coatings.
Applications	ADDpox [®] SR 5198 cured with phenolic or amino resins is suitable for the formulation of solvent containing linings for cans, tubes, and metal containers of all types. It also used in formulation of baking primers and enamels (coil coating) highly resistant to mechanical damage and chemicals. For the formulation of cold-curing coatings it is recommended to use polyisocyanates as hardeners.
Properties	<p>ADDpox[®] SR 5198 features a low colour value and good compatibility with co-resins such as phenolic and amino resins. Container linings and baking enamels yield:</p> <ul style="list-style-type: none"> • Relatively low viscosity • Excellent flexibility and impact resistance • Outstanding deep-drawing capability • Good chemical resistance. <p>Coatings formulated in combination with polyisocyanates exhibit:</p> <ul style="list-style-type: none"> • High solids content can be formulated • High reactivity • Outstanding mechanical properties • Good chemical resistance.

Specific key data	Property	Value	Test method
	Appearance	Clear, no contamination	JCTM 002
	Color, Gardner*	2 max	ASTM D-1544
	Epoxy value	0.34 - 0.42 eq/Kg	ASTM D-1652
	Weight per epoxide	2380 - 2940 g/eq	ASTM D-1652
	Viscosity @ 25°C (77°F)*	3500 - 5500 mPa.s	ISO 12058-1

*40% in butyl carbitol

Specific data are individually checked throughout, guaranteed, and included in the Certificates of Analysis

Typical key data	Property	Value	Test method
	Softening point (Mettler)	~ 150 °C	ASTM D-3461 ISO
	Density at 25 °C	1.18 g/cm ³	8130
	Flashpoint	≥ 200 °C	ISO 2592
	Hydroxyl content	~ 3.1 eq/kg	ISO 4629

Typical key data are spot-checked; the values are typical for the product and are indicated for Information only. The Values are not guaranteed.

As-supplied form	Flakes
Odour	None
Shelf life (at storage temperature between 2-40 °C (see expiry date on original container))	Several years
Hazardous decomposition products (When disposed in fire)	Carbon monoxide, Carbon dioxide and other toxic gases and vapour
Disposal	Regular procedures approved by local authorities.

Package & Storage ADDpox[®] SR 5198 is available in 20 Kg. bags. This product should be stored in a dry place, preferably in the sealed original container, at temperatures between 2 and 40 °C. The product should not be stored exposed to direct sunlight.

Handling Precautions Forced ventilation and dust masks or respirators should be used in order to ensure that operatives do not breath in dust generated by resin, hardener or formulated or powder coatings.

Mandatory and recommended industrial hygiene procedures should be followed whenever our products are being handled and processed. For additional information please consult the corresponding product safety data sheets.

Note ADDpox[®] is a registered trademark of JANA or an affiliate thereof.

Jubail Chemical Industries Co. (JANA)
P.O Box 11919
Jubail Industrial city 31961
Kingdom of Saudi Arabia
Tel : +966 3
3478888
Fax : +966 3 3476705
Website : www.jana-ksa.net

ISO 9001 : 2000



0010737-1044329

DISCLAIMER:

THE INFORMATION AND RECOMMENDATIONS CONTAINED HEREIN ARE BASED UPON OUR DATA BELIEVED TO BE CORRECT. HOWEVER, SINCE THE CONDITIONS OF USE ARE BEYOND OUR CONTROL, NO GUARANTEE OR WARRANTY OF ANY KIND OF EXPRESSED OR IMPLIED IS MADE WITH RESPECT TO THE INFORMATION CONTAINED HEREIN.